

## Technical Data Sheet

Revision Date: 2017-6-10

WHPO\_0004

Name: WANOL F3147

Version: 3.0

### Application

WANOLF3147 is a glycerol based polyether polyol, it is suitable to produce high-resilience PU foam, especially for sponge, high-quality cold-curing PU foam, integral skin foam and many other applications. WANOL F3147 has higher activity, so the foams produced thus have better physical properties.

### Typical Physical Properties

Property	WANOL F3147	Standard
Appearance	Colorless	Q/0600YPU
Color, APHA	≤50	GB/T 22295-2008
Viscosity (25°C), mPa s	500~750	GB/T 12008.7-2010
Water content, %	≤0.05	GB/T 22313-2008
Acid value	≤0.05	GB/T 12008.5-2010
K <sup>+</sup> , ppm	≤3	GB/T 12008.4-2009
Na <sup>+</sup> , ppm	≤3	GB/T 12008.4-2009
PH	5~7	GB/T 12008.2-2010
OHV, mgKOH/g	44.5~47.5	GB/T 12008.3-2009

### Package(s)

Iron drums, IBC tanks, tank wagons and other suitable packages, if necessary.

### Storage

WANOL F3147 should be kept in properly sealed, moisture-tight containers and stored indoors at ambient temperature (15-35°C) in a dry and well-ventilated area. Storage at low temperature (below 5°C) may lead to viscosity increases markedly, and this may cause difficulties in processing. Extended storage at temperatures above 60°C is not recommended to prevent from deterioration of the product quality.

### Shelf Life

Under recommended storage conditions, the shelf life of WANOLF3147 is 12 months since the date of production.

**For more information about safety and environment, please refer to our SDS or contact our customer service center.**

**Version information:**

Release date: November 6, 2015: V 1.0

Revised date: January 20, 2017: revision of V 2.0: corporate update

Revision date: May 10, 2017: revision of V 3.0: company logo changes

**For further information please contact us:**

Address: Wanhua Chemical Group Co., Ltd.

No.17,Tianshan Rd,YEDA,Yantai,264006,China

Customer service: Tel: +86 (535) 8202188 Fax: +86 (535) 683 7242

Web-site: <http://www.whchem.com>

The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products.