

## Technical Data Sheet

Revision Date: 2019-3-30

WHPO\_0018

Name: WANOL F3148P

Version: 1.0

### Application

WANOL F3148P is a polymer polyol, It is suitable to produce flexible slabstock foams, high hardness slabstock foams and hot mould foams. The foams used WANOL F3148P produced thus have better physical properties.

### Typical Physical Properties

Production	WANOL F3148P	Standard
Appearance	White, light yellow or yellow	Q/0600YPU 039-2017
Viscosity (25°C), mPa·s	≤5000	GB/T 12008.7-2010
Moisture, %	≤0.10	GB/T 22313-2008
OHV, mgKOH/g	27.5-33.5	GB/T 12008.3-2009

### Package(s)

Iron drums, IBC tanks, tank wagons and other suitable packages, if necessary.

### Storage

WANOL F3148P should be stored in an inclosed container produced with steel, aluminum, PE or PP, and nitrogen is suggested to fill in the containers. The temperature of the environment should be maintained below 50°C, and avoid sunlight, water and heating. Above 80°C, a deterioration of the product quality would be caused. Short term warming or cooling of the product to low temperatures does not damage the product. It should however be noted that at low temperatures viscosity increases markedly and this may cause difficulties in processing.

### Shelf Life

Under recommended storage conditions, the shelf life of WANOL F3148P is 12 months since the date of production.

**For more information about safety and environment, please refer to our SDS or contact our customer service center.**

### Version information:

Release date: March 30, 2019: V 1.0

**For further information please contact us:**

Address: Wanhua Chemical Group Co., Ltd.

No.17,Tianshan Rd,YEDA,Yantai,264006,China

Customer service: Tel: +86 (535) 820188 Fax: +86 (535) 683 7242

Web-site: <http://www.whchem.com>

The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products.